

**Ressol Chem**

Nr. Meghmani Organics Ltd.  
Plot No. 4615, G.I.D.C.  
Ankleshwar – 393 002.

Manufacture & Supplier Of :

Synthetic Resin, Varnishes,  
Ph. No. ( O ) 02646 – 238145  
( M ) 94279 - 33680.

---

**Product Name:** Bestolkyd FD – 70 (M)

**Type:** Chain Terminated Medium Oil Length Fatty Acid modified Moderate Drying Alkyd Resin.

**Salient Features:** Bestolkyd FD – 70 (M) is formulated for moderate drying application. Soluble in Aliphatic hydrocarbon.

**Applications:** In Clear Varnishes, Insulating Varnishes, Wood Lacquers, Decorative and Industrial Finishes.

**Solubility:** Bestolkyd FD – 70 (M) is soluble in esters, ketones, higher alcohols, ethers, aromatic hydrocarbons.

**Specifications as follows:**

1. Appearance: Yellow Colour Viscous Liquid.
2. Colour: 5 Max. on Gardner Scale
3. Clarity: Clear
4. Viscosity:  $120 \pm 20$  seconds. (By FordCup B4 @ 30°C)
5. % of Non volatile:  $50 \pm 2$  %
6. Acid Value: Max 18.00 mg Koh / gm resin.
7. M.T.T.: 1 : 10 minimum
8. X.T.T.: Infinite
9. Specific Gravity:  $0.99 \pm 0.02$  mg / ml.

**Drying Time:** Touch Dry – 60 to 120 Minutes maximum  
Tack Free – 4 to 6 Hours  
Hard Dry – 24 Hours

**Remarks:** Supplying contains  $70 \pm 2$  % Solid @ 120°C for 2 hours.

**Packing:** 210 Kgs M.S. Barrel and 25 Kgs MS Drum.