

## Ressol Chem

Nr. Meghmani Organics Ltd.  
Plot No. 4615, G.I.D.C.  
Ankleshwar – 393 002.

Manufacture & Supplier Of :

Synthetic Resin, Varnishes,  
Ph. No. ( O ) 02646 – 238145  
( M ) 94279 - 33680.

---

**Product Name:** Bestolkyd FD – 70 (X)

**Type:** Chain Terminated Short Oil Length Fatty Acid modified Fast Drying Alkyd Resin.

**Salient Features:** Bestolkyd FD – 70 (X) is formulated for fast drying application by spray or brushing for automotives and industrial use. Excellent Resistance to yellowing in light and heat.

**Applications:** In Automotive refinishes, Industrial and Decorative paints and Insulating Varnishes.

**Solubility:** Bestolkyd FD – 70 (X) is soluble in esters, ketones, higher alcohols, ethers, aromatic hydrocarbons.

### Specifications as follows:

1. Appearance: Yellow Colour Viscous Liquid.
2. Colour: 5 Max. on Gardner Scale
3. Clarity: Clear
4. Viscosity:  $120 \pm 20$  seconds. (By FordCup B4 @ 30°C)
5. % of Non volatile:  $50 \pm 2$  %
6. Acid Value: Max 20.00 mg Koh / gm resin.
7. M.T.T.: Nil
8. X.T.T.: Infinite
9. Specific Gravity:  $0.95 \pm 0.02$  mg / ml.

**Drying Time:** Touch Dry – 5 Minutes

Tack Free – 120 Minutes with thumb impression

Hard Dry – 24 Hours

**Remarks:** Supplying contains  $70 \pm 2$  % Solid @ 120°C for 2 hours.

**Packing:** 210 Kgs M.S. Barrel and 25 Kgs MS Drum.