

Ressol Chem

Nr. Meghmani Organics Ltd.
Plot No. 4615, G.I.D.C.
Ankleshwar – 393 002.

Manufacture & Supplier Of :

Synthetic Resin, Varnishes,
Ph. No. (O) 02646 – 238145
(M) 94279 - 33680.

Product Name: Bestolkyd FD – 70 (XF)

Type: Chain Terminated Short Oil Length Fatty Acid modified Fast Drying Alkyd Resin.

Salient Features: Bestolkyd FD – 70 (XF) is formulated for fast drying tac free application. Excellent hardness, durability and Resistance to yellowing in light and heat.

Applications: In Clear Varnishes, Insulating Varnishes, Automotive refinishes, Industrial and Economical PU Coatings.

Solubility: Bestolkyd FD – 70 (XF) is soluble in esters, ketones, higher alcohols, ethers, aromatic hydrocarbons.

Specifications as follows:

1. Appearance: Yellow Colour Viscous Liquid.
2. Colour: 6 Max. on Gardner Scale
3. Clarity: Clear
4. Viscosity: 120 ± 20 seconds. (By FordCup B4 @ 30°C)
5. % of Non volatile: 50 ± 2 %
6. Acid Value: Max 20.00 mg Koh / gm resin.
7. M.T.T.: Nill
8. X.T.T.: Infinite
9. Specific Gravity: 0.99 ± 0.02 mg / ml.

Drying Time: Touch Dry – 5 Minutes
Tack Free – 120 Minutes
Hard Dry – 24 Hours

Remarks: Supplying contains 70 ± 2 % Solid @ 120°C for 2 hours.

Packing: 210 Kgs M.S. Barrel and 25 Kgs MS Drum.