Ressol Chem

Nr. Meghmani Organics Ltd. Plot No. 4615, G.I.D.C. Ankleshwar – 393 002.

Product Name: Type:	Bestolkyd SD – 40 Semi Drying Oil modified Glycerol Phthalate Short oil Length Alkyd Resin.
Salient Features:	Bestolkyd SD – 40 is Short oil length Oil modified alkyd resin for non yellowing primers and paints with good gloss and gloss retention.
Applications:	In Clear Varnishes and Primers, Cold Catalyzed Wood Finishes, N.C. Lacquers and Paints, Stoving Paints and Industrial Finishes.
Solubility:	Bestolkyd SD – 40 is soluble in esters, ketones, higher alcohols, ethers, aromatic hydrocarbons.

Specifications as follows:

1. Appearacne	Pale Yellow Colour Liquid.
2. Colour:	3 Max. on Gardner Scale
3. Clearity:	Clear
4. Viscosity:	60 ± 15 seconds. (By FordCup B4 @ 30° C)
5. % of Non volatile:	$45\pm2\%$
6. Acid Value:	Max 10.00 mg Koh / gm resin.
7. M.T.T.:	1 : 2 Minimum
8. X.T.T.:	1 : 10 Minimum
9. Specific Gravity:	$0.97 \pm 0.01 \text{ mg} / \text{ml}.$

Remarks: Supplying contains 70 ± 2 % Solid @ 120° C for 2 hours.

Packing: 210 Kgs M.S. Barrel and 25 Kgs MS Drum.