

Ressol Chem

Nr. Meghmani Organics Ltd.
Plot No. 4615, G.I.D.C.
Ankleshwar – 393 002.

Manufacture & Supplier Of :

Synthetic Resin, Varnishes,
Ph. No. (O) 02646 – 238145
(M) 94279 - 33680.

Product Name: Bestolkyd SS – 40

Type: Unsaturated Fatty Acid modified Glycerol
Phthalate Resin.

Salient Features: Bestolkyd SS – 40 is Short oil length unsaturated fatty acid modified alkyd resin with good hardness and non oxidizing properties with good color retention.

Applications: In Clear Varnishes and Primers, Cold Catalyzed Wood Finishes, N.C. Lacquers and Paints, Stoving Paints and Industrial Finishes.

Solubility: Bestolkyd SS – 40 is soluble in esters, ketones, higher alcohols, ethers, aromatic hydrocarbons.

Specifications as follows:

1. Appearance: Light Yellow Colour Liquid.
2. Colour: 2 Max. on Gardner Scale
3. Clarity: Clear
4. Viscosity: 50 ± 15 seconds. (By FordCup B4 @ 30°C)
5. % of Non volatile: 45 ± 2 %
6. Acid Value: Max 10.00 mg Koh / gm resin.
7. M.T.T.: 1 : 2 Minimum
8. X.T.T.: 1 : 10 Minimum
9. Specific Gravity: 0.98 ± 0.01 mg / ml.

Remarks: Supplying contains 70 ± 2 % Solid @ 120°C for 2 hours.

Packing: 210 Kgs M.S. Barrel and 25 Kgs MS Drum.