

Ressol Chem

Nr. Meghmani Organics Ltd.
Plot No. 4615, G.I.D.C.
Ankleshwar – 393 002.

Manufacture & Supplier Of :

Synthetic Resin, Varnishes,
Ph. No. (O) 02646 – 238145
(M) 94279 - 33680.

Product Name: Bestomine MF 600

Type: Synthetic Amino Resin – Butylated Melamine
Formaldehyde Resin.

Salient Features: MF 600 is Normal Butanol base Moderate reactive Melamine formaldehyde Resin with excellent hardness, reactivity and Good color retention.

Applications: Mainly used for high gloss general purpose stoving enamels. Used in D.G. lacquer for coating metallised polyester films and in clear stoving lacquers.

Solubility: Bestomine MF 610 is soluble in alcohols, esters, ketones, glycol ethers, aromatic hydrocarbons.

Specifications as follows:

1. Appearance: Colorless water white Liquid.
2. Colour: 1 Max. on Gardner Scale
3. Clarity: Clear
4. Viscosity: 60 ± 15 seconds. (By Ford Cup B 4 @ 30°C)
5. % of Non volatile: 55 ± 2 %
6. Acid Value: Max 1.00 mg Koh / gm resin.
7. Free Formalin: 2% Max.
8. M.T.T.: 200 - 400 %
9. X.T.T.: Infinite
10. Specific Gravity: 1.01 – 1.03
11. Electric Resistivity: 300 KOhms Maximum.

Remarks: Supplying contains 65 ± 2 % Solid @ 120°C for 2 hours and 12 poise to 22 poise viscosity.

Packing: 210 Kgs M.S. Barrel and 25 Kgs MS Drum.