

Ressol Chem

Nr. Meghmani Organics Ltd.
Plot No. 4615, G.I.D.C.
Ankleshwar – 393 002.

Manufacture & Supplier Of :

Synthetic Resin, Varnishes,
Ph. No. (O) 02646 – 238145
(M) 94279 - 33680.

Product Name: Bestomine MF 680

Type: Synthetic Amino Resin – Butylated Melamine
Formaldehyde Resin.

Salient Features: MF 680 is Mix Butanol base High reactive Melamine formaldehyde Resin with excellent hardness, good color retention and exterior durability.

Applications: Stoving Finishes for Automotive and Electric Goods and Appliances for kitchen and hospital. Low temperature curing with Cold Catalyst for plastic and others articles. Used along with thermosetting acrylic resin.

Solubility: Bestomine MF 680 is soluble in alcohols, esters, ketones, glycol ethers, aromatic hydrocarbons.

Specifications as follows:

- | | |
|---------------------------|--|
| 1. Appearance | Colorless water white Liquid. |
| 2. Colour: | 1 Max. on Gardner Scale |
| 3. Clarity: | Clear |
| 4. Viscosity: | 60 ± 15 seconds. (By Ford Cup B 4 @ 30°C) |
| 5. % of Non volatile: | 50 ± 2 % |
| 6. Acid Value: | Max 1.00 mg Koh / gm resin. |
| 7. Free Formalin: | 3% Max. |
| 8. M.T.T.: | 300 - 800 % |
| 9. X.T.T.: | Infinite |
| 10. Specific Gravity: | 1.01 – 1.03 |
| 11. Electric Resistivity: | 300 KOhms Minimum. |

Remarks: Supplying contains 62 ± 2 % Solid @ 120°C for 2 hours and 17 poise to 22 poise viscosity.

Packing: 210 Kgs M.S. Barrel and 25 Kgs MS Drum.